

Physical properties		Standard
Density	> 99.5% > 6.02 g/cm ³	ISO 18754
Purity	> 99.5%	
Mechanical properties		
Hardness	>1260 HV	ASTM C1327
Shrinkage	Linear 17.8% per axis (isotropic)	
Young's Modulus of Elasticity	215 GPa	ASTM E494-20
Fracture Toughness	4.5 MPa · m ^{1/2}	
Poisson's Ratio	0.31	ASTM C818
Thermal properties		
Thermal Conductivity	3 W/(m · K)	ASTM C408
Coefficient of liner thermal expansion	10 (40-400°C) ppm/°C E-6 11 (40-800°C) ppm/°C E-6	ASTM C372
Specific Heat Capacity	0.46 J/(Kg · K)	ASTM C351
Thermal Shock resistance (Temperature Difference)	150 °C	
Electrical properties		
Volume Resistivity	20°C - 1.5E+12 Ω · cm 300°C - 8.3E+06 Ω · cm 500°C - 8.8E+06 Ω · cm	ASTM D257
Dielectric Strength	11 kV/mm	ASTM D149
Dielectric Constant (1 MHz)	34	ASTM D150
Dissipation Factor	0.0096 (1KHz)	ASTM D150
Others		
MSDS availability	EU, US, RU	
Certifications	ISO 9001, ISO 13485	
Cartridge Weight	3Kg	
Storage conditions	15 - 35°C; < 50% relative humidity, non-condensing	
Suitable protection	As per instructions on the cartridge	
Risk phrases	P264 Wash thoroughly after handling. P280 Wear protective gloves/protective clothing/eye protection/face protection. H319 Causes serious eye irritation	
First aid	As per instructions on the cartridge	
Shelf life	1 year at room temperature	



All data provided herein is for information purposes only, is provided on an "as is" basis, without warranty of any kind, express or implied, and should not be relied upon or considered specific advice to any customer project. Any product and materials information provided herein is subject to terms and conditions as may be agreed upon by XJet in writing. All measurements, to the extent detailed, are based on internal testing made on lab specimens by XJet or on its behalf, and the actual performance or results of any product may vary. XJet reserves the right to change the terms and conditions under which its products are offered at any time.